



V	R	B																									
			0.5	0.8	1	1.2	1.5	2	2.5	3	4	5	6	8	10	12	15	20	25	30							
4	0.7	2.6	40	100									T = 420-480 N/mm² (C=1) P(kN/m)														
6	0.9	3.9	26	69	106	153																					
8	1.5	5.2	20	55	80	115	180																				
10	1.7	6.5		41	65	95	145	260																			
12	2	7.8			55	80	120	215	335																		
16	2.7	10.4				60	90	160	250	360																	
20	3.4	13					75	130	200	290	520																
24	3.9	15.6						106	166	240	426	666															
30	5	20							140	190	340	540	770														
35	6	23								170	300	460	660														
40	7	26								150	260	400	580	1030													
50	8.5	32									210	320	460	820	1280												
55	9	36										300	420	750	1170												
60	10	39										270	390	690	1070												
70	11.7	45											330	590	920	1320											
80	13.5	52												290	520	800	1160	1800									
90	15	58													460	710	1030	1600									
100	17	65													410	640	930	1440									
120	20	78														540	770	1200									
140	24	91															660	1030	1830								
200	31	130																719	1278	1997							
250	39	163																	1022	1598	2300						
300	47	195																	852	1331	1917						
350	55	228																		1141	1643						

C

P'=PxC

Nota: Valor marcado en amarillo es para acero al carbono

1

2,2

2,0

1,80

1,55

1,35

1,1

0,9

0,65

0,45

200

300

400

450

500

600

700

800

900

1000

T (N/mm²)

Conversión:

1Kn = 0.102TonF

